



OIL MONOGLYCERIDES

Product Nomenclature	Type	Appearance	S. D. S Tolerance	Recommended Usages
Repleic 131	Linseed oil monoglyceride	Pale Yellow	1 : 10 Min.	As pigment dispersion agent for darker shade of paints
Repleic 132	Coconut oil monoglyceride	Pale Yellow	1 : 10 Min.	As pigment dispersion agent for lighter shades of paints

POLYISOCYANATES RESINS

Product Nomenclature	Type	Colour (Gardner/ Appearance)	Viscosity at 25°C on Gardner (in stokes)	Isocyanate Content (%)	% Non-volatiles at 12°C / 1 hr	Recommended Usages
Replacure 152	Aromatic isocyanate adduct in ethyl acetate	3 Max.	10-22	13±0.5	74±1	Laminating adhesive, sealants chemicals and abrasion resistant coatings, coatings for sports goods
Replacure 167	Aromatic isocyanate adduct in ethyl acetate	2 Max.	12.9-22.7	11.9±0.4	67±2	Laminating adhesive, sealants chemicals and abrasion resistant coatings, coatings for sports goods
Replacure 171	Aliphatic isocyanate adduct in ethyl acetate	2 Max.	1.65-2.25	16.5±1	75±1.5	Good exterior durability, colour/gloss retention

RESINS & PLASTICS LTD.

Regd. Off.: Plot No. A-8, Marol Industrial Estate of MIDC, Cross Road B, Street No.5, Andheri (E), Mumbai - 400 093, India. Tel.: +91- 22- 6198 7000 Email : info@resplast.com

Although the information contained in this Product Data Sheet is believed to be correct as of the date hereof, Resins & Plastics Ltd. makes no representation the completeness of accuracy in this Data Sheet. Those who use this product described herein must determine the appropriate manner for processing the product to ensure the safety and quality. In no event shall Resins & Plastics Ltd. be responsible for damages of any nature resulting from the use of or reliance upon the information contained herein.